

# BC 709 Polyol and BC 768 Isocyanate

## Product Description:-

This system design for shoe production with the density of 0.25 to 0.4 g per cubic metre. It has higher flexibility with more than 150000 steps as compared to 25000 steps of regular PU systems

### TYPICAL REACTION CHARACTERISTICS:

Cream Time	25 SECONDS
Gel Time	150 SECONDS
Free Rise Density	36 kg/m <sup>3</sup>

### COMPOUND CHARACTERISTICS:

Polyol Viscosity	800 mPa.S at 25 degree Celsius
Isocyanate Viscosity	210 mPa.S at 25 degree Celsius
NCO Content	31 % BY WEIGHT

### Typical Polymer Properties:

Density	42-45 kg/m <sup>3</sup>
Fire Rating	B2 according to DIN 4102
Compressive Strength	110 KPA
Dimensional Stability	LESS THAN 1 PERCENT
Thermal Conductivity	0.023 Watt/m.K

### SHELF LIFE:-

Polyol Compound: 6  
months Isocyanate  
Compound: 6 months

Always store the drums before use at a temperature between 15 °C and 35 °C,

#### Building Chemistry Industry

2<sup>nd</sup> Industrial Area Dammam .Kingdom of Saudi Arabia.

Email: [info@bcisaudi.com](mailto:info@bcisaudi.com) Website: [www.bcisaudi.com](http://www.bcisaudi.com)



always in dry areas, without the possibility of moisture entering, and without direct contact with the sun or heat sources, otherwise they may be affected its reactivity and performance. Low ambient temperature increases the viscosity of the polyol, which makes it difficult to mix and apply, which can cause its mixing ratio to vary and the consequent internal problems in the mixing and application equipment.

## HEALTH AND SAFETY PRECAUTIONS

- Respiratory Protection: When handling or spraying use an air-purifying respirator.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking, or smoking.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air.
- Waste: Waste generation should be avoided or minimized.
- Incinerate under controlled conditions in accordance with local laws and national regulations.
- Re-occupancy of the work site without respiratory equipment is minimum 24 hours providing the correct ventilation for the area sprayed.
- Contractors and applicators must comply with all applicable and appropriate guidelines for storage and safety guidelines.

Anyway, consult the material safety data sheet

### **Packing:-**

BC 702 Spray 45 Polyol     **220 Kgs**  
BC 768 Iso cyanate         **250 Kgs**

The Technical specification information and recommendation given one based on the current technical knowledge and the user or his representative is recommended to check the suitability of the product Building chemistry industry reserves the right to amend the technical characteristic of the product as part of ongoing research and development. As the work execution is beyond the direct and continuous control of Building chemistry industry no guarantee and or responsibility is assumed on the performance of work completion executed with use of our products.

### **Building Chemistry Industry**

2<sup>nd</sup> Industrial Area Dammam .Kingdom of Saudi Arabia.  
Email: [info@bcisaudi.com](mailto:info@bcisaudi.com) Website: [www.bcisaudi.com](http://www.bcisaudi.com)

