

BC Tec Brush Coat

Description:-

BC Tec Brush Coat is a prepackaged cementitious brush, or roller applied surfacing material. Modified with a high solids latex, this material exhibits excellent bond strength with reduced permeability. BC Tec Brush Coat forms a breathable protective coating. B Tec Brush Coat protects exposed reinforced concrete structures from attack from acidic gases and chloride ions. The coating is particularly suitable for use in areas of coastal and marine environments and can be used in all types of structures, for existing and new concrete. BC TEC BRUSH Coat exhibits high wear resistance, weather resistance and is suitable to be used as a decorative coating. The coating provides seamless resilient waterproofing which is suitable for reservoirs, roofs, & water tanks.

Feature & Benefits:

Suitable for waterproofing water retaining structures.

Polymer modification reduces permeability and dusting while increasing bond, tensile and flexural strength.

Excellent resistance against the Middle East Environment.

Non-toxic

For interior or exterior use

Excellent wear resistance. User friendly - low labor cost.

Bond Strength	3.6 Mpa
Compressive Strength	5600 psi
Flexural Strength	1600 psi
Toxicity	Non-toxic
Density	1.7gm/Cm3
Tensile Strength	725 psi

Directions For Use

Surface Preparation:

Concrete must be clean and rough. All oil, dirt, debris, paint and unsound concrete must be removed. The surface can be prepared mechanically using sandblasting, shot blasting or scarifier which will give a slight surface profile. The final step in cleaning should be complete removal of all residue with a vacuum cleaner or by pressure washing. Acid etching is acceptable only when mechanical preparation is impractical. It is recommended that only contractors experienced in the acid etching process use this means of surface preparation. The salt of the reaction must be thoroughly pressure

Building Chemistry Industry

Suit No 203, Al Manar Business park Bin Khalid Street Dammam .Kingdom of Saudi Arabia.

Email: info@bcisaudi.com Website: www.bcisaudi.com



washed away. Prior to application, the surface should be pre-soaked with clean water, excess standing water should be removed.

Note:

Even with proper procedures an acid etched surface may not provide strong bond as produced by mechanical preparation procedures. All concrete must possess an open surface texture with all curing compounds and sealers removed. All cracks over 2mm wide should be routed out to a 6 mm width and 6mm depth and patched and repaired prior and patched and repaired to application of BC Tec Brush coat.

Mixing:

BC TEC BRUSH COAT should be mixed using slow speed mixer. Use a paddle type mortar mixer for large jobs. Add the appropriate amount of liquid for the batch size and then add the dry product. Mix for a minimum of 3 minutes, endeavor to avoid air entrapment. BC TEC BRUSH COAT should be placed immediately after mixing, avoid mixing more material that can be used within 45 minutes. For the Middle East climatic conditions, where the temp. exceeds 40 ° C , use of a primer coat of BC TEC BRUSH COAT powder and water mixed in a slurry like consistency. Apply BC TEC BRUSH COAT directly over the slurry/primer coat.

Cleaning:

Use clean water for cleaning of equipment and tools.

Coverage:

One kit of BC TEC BRUSH Coat covers 18m²at 1 mm thickness. If BC TEC BRUSH COAT is to be subjected to light foot traffic minimum thickness should be 2 mm.

Packaging:

Available In Packaged As 20 Kg Powder and 10 Liters of Latex Additives.

Colours:

White & Grey

The Technical specification information and recommendation given one based on the current technical knowledge and the user or his representative is recommended to check the suitability of the product Building chemistry industry reserves the right to amend the technical characteristic of the product as part of ongoing research and development. As the work execution is beyond the direct and continuous control of Building chemistry industry no guarantee and or responsibility is assumed on the performance of work completion executed with use of our products.

Building Chemistry Industry

Suit No 203, Al Manar Business park Bin Khalid Street Dammam .Kingdom of Saudi Arabia.

Email: info@bcisaudi.com Website: www.bcisaudi.com

